


707 West 26th Avenue  
Covington LA 70433  
800.354.4154  
985.892.7196 fax


KYNAR 500® or HYLAR 5000®



Regal White



New Bone White



Stone White



Sandstone



Surrey Beige



Dark Bronze



Patina Green



Hemlock Green



Classic Green



Hartford Green



Colonial Red



Banner Red\*



Terra Cotta



Teal



Slate Blue



Regal Blue



Old Town Gray




Slate Gray



Charcoal Gray




Matte Black



Mansard Brown



Medium Bronze



Musket Gray



Burgundy



Apothecary Blue



Pewter\*



Bright Silver\*



Bright Copper\*

*Colors shown are as close to actual colors as allowed by the printing process. Actual metal samples are available.*

*Due to product improvements, changes and other factors, we reserve the right to change or delete information herein without prior notice.*

## Flat Sheet Color Availability

	Steel			Aluminum			
	24ga	22ga	18ga	.032"	.040"	.050"	.063"
Regal White	•	•	•	•			•
New Bone White	•	•		•	•	•	
Stone White	•			•	•	•	
Sandstone	•	•		•	•	•	
Surrey Beige	•	•		•	•	•	
Old Town Gray	•						
Slate Blue	•						
Colonial Red	•			•			
Banner Red	•						
Dark Bronze	•	•	•	•	•	•	•
Hartford Green	•			•			
Slate Gray	•			•	•		
Patina Green	•			•			
Regal Blue	•			•			
Charcoal Gray	•						
Hemlock	•						
Classic Green	•			•	•		
Matte Black	•			•	•		
Terra Cotta	•						
Teal	•						
Pewter	•						
Bright Copper	•						
Bright Silver	•						
Mansard Brown	•			•	•	•	
Medium Bronze	•			•	•	•	
Musket Gray	•						
Burgundy	•						
Apothecary Blue	•						

*Notes on availability:*

1. Standard inventory is non-embossed. Please contact us for the availability of stucco embossing.
2. Protective strippable film is available upon request.
3. Banner Red, Pewter, Bright Copper and Bright Silver are available on an inquiry basis and subject to premium pricing.

Paint Performance Properties	Hot Dipped Galvanized Steel or Galvalume	Aluminum
<b>Accelerated Weathering</b> ASTM D 4587 (Dew Cycle Weatherometer)	Hours: 3,000 Total Chalk: Rating 8 Color: 5ΔE Hunter units max	Hours: 3,000 Total Chalk: Rating 8 Color: 5ΔE Hunter units max
ASTM G 23	Hours: 5,000 Total Chalk: Rating 8 Color: 5ΔE Hunter units max	Hours: 5,000 Total Chalk: Rating 8 Color: 5ΔE Hunter units max
<b>Salt Spray</b> ASTM B 117	Hours: 1,000 Total Scribe: Rating 7 1/16"(1.6mm) Field: Rating 10, no blisters	Hours: 3,000 Total Scribe: Rating 10, no creepage Field: Rating 10, no blisters
<b>Humidity</b> ASTM D 2247	Hours: 2,000 Total Rating: 10, no blisters	Hours: 3,000 Total Rating: 10, no blisters
<b>Formability</b> ASTM D 4145	2T	2T
ASTM D 522 (Elongation over 1/8" mandrel)	No cracking No loss of adhesion	No cracking No loss of adhesion
<b>Pencil Hardness</b> ASTM D 3363	HB-2H	HB-2H
<b>Abrasion Resistance</b> ASTM D 968	50-80 Liters of falling sand	50-80 Liters of falling sand
<b>Specular Gloss</b> ASTM D 523	20-35 at 60°*	20-35 at 60°*
<b>Reverse Impact</b> ASTM D 2794	3 x Metal thickness in inch-lbs. No loss of adhesion	1 1/2 x Metal thickness in inch-lbs. No loss of adhesion
<b>Flame Test</b> ASTM E 84	Class A rated coating	Class A rated coating

\* Lower gloss coatings are available

Standard architectural colors and finishes feature 70% KYNAR 500® & HYLAR 5000® polyvinylidene fluoride (PVDF) resin paint systems to ensure long term color retention and performance. Custom colors and finishes are also available. Minimum quantities and set-up charges may apply.

Kynar 500 is a registered trademark of Elf Atofina.  
Hylar 5000 is a registered trademark of Ausimont USA.